

9



Europäisches Patentamt

European Patent Office

Office européen des brevets

Publication number:

**0 292 702
A1**

10

EUROPEAN PATENT APPLICATION

Application number: **88106425.7**

Int. Cl. 4: **C09D 17/00 , C09B 67/00**

Date of filing: **23.12.85**

Priority: **25.12.84 JP 278891/84**

Date of publication of application:
30.11.88 Bulletin 88/48

Publication number of the earlier application in
accordance with Art.76 EPC: **0 186 189**

Designated Contracting States:
DE FR GB IT

Applicant: **Nippon Paint Co., Ltd.**
2-1-2, Oyodokita Oyodo-ku
Osaka-shi Osaka-fu(JP)

Inventor: **Gouji, Harunori**
7-23 Kosakahonmachi 1-chome
Higashiosaka-shi Osaka-fu(JP)
Inventor: **Kato, Hisao**
39-7, Nishikinya 2-chome
Hirakata-shi Osaka-fu(JP)
Inventor: **Kataoka, Hiroyoshi**
10-19, Hiyoshidai 2bancho
Takatsuki-shi Osaka-fu(JP)

Representative: **Dr. Elisabeth Jung Dr. Jürgen**
Schirdewahn Dipl.-Ing. Claus Gernhardt
P.O. Box 40 14 68 Clemensstrasse 30
D-8000 München 40(DE)

Composition containing dispersed pigment.

A composition containing dispersed pigment comprises, as a dispersing agent, a reaction product of at least one of the polyamines selected from the group consisting of ethylene diamine, 1,3-propylene diamine, hexamethylene diamine, diethylene triamine, triethylene tetramine, tetraethylene pentamine, pentaethylene hexamine, bisaminopropyl piperadine, bisamino pyridine, xylylene diamine, metaphenylene diamine, 4,4'-diaminodiphenyl methane and polyethyleneimine, and at least one of the polyisocyanates having two or more isocyanate groups.

EP 0 292 702 A1

Composition containing dispersed pigment

BACKGROUND OF THE INVENTION

FIELD OF THE INVENTION

This invention concerns a composition containing pigment dispersed in a reaction product of polyamines and polyisocyanates. More particularly, this invention relates to a composition containing at least a pigment dispersed in a dispersing agent, which possesses excellent dispersion stability of the pigment, lower thixotropy and an excellent flow property.

DESCRIPTION OF THE PRIOR ART

In conventional compositions containing dispersed pigments composed of pigments, resins and solvents, if the dispersibility of the pigment to the resin is poor, the composition containing the dispersed pigment exhibits remarkable thixotropy due to the flocculation of the pigment. Further, since paint films formed by applying a composition containing a dispersed pigment having flocculated pigments cause various problems such as degradation in the gloss, decrease in the distinctness of image, reduction in the color strength, flooding, etc., sufficient performance of the pigment can be obtained with such composition containing the dispersed pigment.

In order to overcome the foregoing problems, various inventions have been proposed as described below.

(1) There has been a method of incorporating certain pigments derivatives into pigment as shown in Japanese Patent Laid-Open No. 18736/1976, but this method can not be applied to general use for various pigments since such pigment derivatives are colored by those structure.

(2) It has also been disclosed, for example, in Japanese Patent Laid-Open No. 160396/1975 and British Patent Specification Nos. 1393401 and 1393402 a technique of utilizing, as a dispersing agent, those compounds obtained by reacting three groups of compounds, that is, organic compounds having at least two isocyanate groups, i.e., polyisocyanates (group A), organic compounds having at least two functional groups reactive with the isocyanate groups, for example, amino groups or hydroxyl groups (group B) and polymers (group C) having one functional group reactive with the isocyanate groups. These dispersing agents have, however, the defect as described below.

The design concept for the dispersing agent of this type is to prepare a block structure comprising chains that can be solvated with solvents and polar anchor group portions adsorptive to the pigment as stated by A. Topham in "Progress in Organic Coatings", Vol. 5, (1977), pp 237 - 243. When employing this technique, it is necessary to prepare a composition containing dispersed pigment comprising the dispersing agent as described above, the solvent and the pigment and, in the case of preparing paints by using the composition, it is generally further necessary to add various type of resins as the film forming vehicles. In this case, the type and amount of vehicle resins to be added as the film forming ingredients are restricted in view of compatibility between the film forming resins and the polymer constituting the dispersing agent. Accordingly, it has been difficult to use such dispersing agents for general purpose application. Particularly, they have insufficient effect for the pigments with poor dispersibility, for example, quinacridone pigments. Further, problems may occur in the durability or other areas of film performance of the paint films containing a large amount of dispersing agent used for dispersing pigments as described in the prior art and literature. A certain complexity of the production steps required to utilize these prior technique is imposed, such as the requirement for the prior synthesis of the dispersing agent, as well as the prior synthesis of the ingredients, that is, the polymers of the group C necessary for synthesizing the dispersing agent.

Moreover, the conventional dispersing agents have previously been synthesized and have been used by being blended with pigments and vehicle resins upon dispersing the pigments. Since the conventional dispersing agents have been prepared and used in these ways, when they are used, for example, for the preparation of paints, they produce undesirable effects on the paints and the condition of the paint films due

to the restriction caused from the composition of the dispersing agents, such as poor compatibility between the dispersing agents and the vehicle resins, restrictions on the types of solvents to be used or reduction in the water resistance of the paint films.

5

SUMMARY OF THE INVENTION

It is one object of the invention to provide a composition containing dispersed pigment having an excellent dispersion stability for the pigments.

10 The term "dispersion stability" used herein means that a pigment can be finely dispersed and that the dispersed pigment is present, in a stable state with no flocculation.

This invention concerns a composition containing a dispersed pigment comprising as a dispersing agents, one or more reaction products obtained from at least one organic compound having two or more primary amino groups and/or secondary amino groups (hereinafter referred to as polyamines) and at least 15 one polyisocyanate having two or more isocyanate groups (hereinafter referred to as polyisocyanates) wherein the polyamines are selected from the group consisting of ethylene diamine, 1,3-propylene diamine, hexamethylene diamine, diethylene triamine, triethylene tetramine, tetraethylene pentamine, pentaethylene hexamine, bisaminopropyl piperadine, bisamino pyridine, xylylene diamine, metaphenylene diamine, 4,4'-diaminodiphenyl methane and polyethyleneimine.

20 In another aspect, this invention concerns a composition containing dispersed pigment, which comprises pigments, vehicle resins, reaction products as described above and, optionally, organic solvents.

DETAILED DESCRIPTION OF THE INVENTION

25

(Pigments)

30 In this invention, various types of inorganic pigments or organic pigments that are usually employed in the paint or printing ink industry can be used. The inorganic pigments can include, for example, zinc white, titanium dioxide, antimony white, iron oxide red, iron oxide yellow, transparent iron oxide, red lead, cadmium yellow, zinc sulfide, lithopone, barium sulfate, lead sulfate, barium carbonate, white lead, alumina white and carbon black. The organic pigments can include, for example, various pigments such as azo 35 series, polycondensation azo series, metal complex azo series, benzimidazolone series, phthalocyanine blue series, phthalocyanine green series, thioindigo series, anthraquinone series, flavanthrone series, indanthrene series, anthrapyrimidine series, pyranthrone series, isoindolinone series, perylene series, perinone series and quinacridone.

40 While this invention is mainly directed, among those described above, to the use of carbon black and organic pigments which have been considered as difficult to disperse pigments, this invention can of course be applied also to other pigments with improved dispersibility of the pigments.

(Resins)

45


As the vehicle resins usable in this invention, those vehicle resins usually employed in the preparation of paints and printing inks can advantageously be used and include, for example, alkyd resins, polyester resins, acrylic resins, vinyl resins such as polyvinyl chloride, polyvinyl acetate, chlorinated polyolefins and polyamide resins.

50

55

(Polyamines)




Among the selected polyamines, those having three or more of primary and/or secondary amino groups or those polyamines having two or more primary and/or secondary amino groups and one or more tertiary amino groups are used preferably. Preferred polyamines include, for example, diethylenetriamine, triethylenetetramine, tetraethylenepentamine, pentaethylenehexamine, polyethyleneimine prepared through cationic polymerization of ethyleneimine, that is, commercially available polyethyleneimine represented by the structure as shown in the following formula (A), bisaminopropyl piperazine and bisaminopyridine :









(Polyisocyanates)

The polyisocyanates usable in this invention can include, for example, those diisocyanate compounds such as tolylene diisocyanate (TDI), 4,4-diphenyl methane diisocyanate (MDI), xylylene diisocyanate (XDI), hexamethylene diisocyanate, hydrogenated MDI, hydrogenated TDI, hydrogenated XDI and isophorone diisocyanate. More preferably, the use of higher polyfunctional polyisocyanate compounds is advantageous.

Such compounds can include, for example, those compounds prepared by reacting polyols with diisocyanates such as represented by formulas (1) - (4), those compounds prepared through biuret reaction from diisocyanates, for example, represented by formula (5), those compounds prepared through the ring formation of diisocyanates such as compounds represented by the formulas (6) - (8) and those compounds represented by the formulas (9) and (10).







45 where n represents an integer from 1 to 4.

Commercially available products containing the above-mentioned compounds as the main ingredient are exemplified as described below.

Coronate HL (trade name of products available from Nippon Polyurethane Industries Co., Ltd.) containing the compound of formula (1) as the main ingredient.

50 Sumidur L (trade name of products available from Sumitomo Bayer Urethane Co., Ltd.) containing the compound of formula (2) as the main ingredient.

Takenate D 110N (trade name of products available from Takeda Chemical Industries Co., Ltd.) containing the compound of formula (3) as the main ingredient.

55 Takenate D-120N (trade name of products available from Takeda Chemical Industries Co., Ltd.) containing the compound of formula (4) as the main ingredient.

Takenate D-165N, Takenate D-165N-90CX (trade name of products available from Takeda Chemical Industries Co., Ltd.), Sumidur N (trade name of products available from Sumitomo Bayer Urethane Co., Ltd.) containing the compound of formula (5) as the main ingredient.

Coronate EH (trade name of products available from Nippon Polyurethane Industries Co., Ltd.) containing the compound of formula (6) as the main ingredient.

Desmodule IL (trade name of products available from Bayer AG) containing the compound of formula (7) as the main ingredient.

5 Desmodule HL (trade name of products available from Bayer AG) containing the compound of formula (8) as the main ingredient.

Desmodule R (trade name of products available from Bayer AG) containing the compound of the formula (9) as the main ingredient.

10 Millionate MR (trade name of products available from Nippon Polyurethane Industries Co., Ltd.) containing the compound of the formula (10) as the main ingredient.

Each of the commercial products is not a pure chemical but a mixture of a compound of the structure shown by each of the formulas as the main ingredient and a compound of a structure similar to that of the main ingredient, and the respective products have an average number of functional groups (number of isocyanate groups per average molecular weight) of from 2.5 to 6.

15

(Organic Solvents)

20 The solvents usable in this invention are those ordinarily employed in the paint and printing ink industries, and can include, for example, hydrocarbon series solvents such as toluene, xylene, Solvesso 100 and Solvesso 150 (trade name of products available from Esso Standard Co. Ltd.), ester series solvents such as ethyl acetate and butyl acetate, ketone series solvents such as methyl ethyl ketone and methyl isobutyl ketone and ether series solvents such as ethylene glycol monoethyl ether and ethylene glycol mono-normal butyl ether. These solvents may be used alone or as a mixture of two or more different
25 solvents.

(Mixing Ratio of Polyamines and Polyisocyanates)

30 The polyamines and polyisocyanates are preferably used in such a blending ratio as primary and/or secondary amino groups are present at least in an amount equivalent to the isocyanate groups, and it is generally preferred to use the amino groups in excess of an amount equivalent to the isocyanate groups.

In the case of using polyamines containing the primary and/or secondary amino groups with an excess blending of the amino groups to the isocyanate groups, it is generally advantageous to use and blend
35 polyamines containing three or more primary and/or secondary amino groups such that at least two of the amino groups can react with the isocyanate groups.

In the case of using polyamines containing primary and/or secondary amino groups and tertiary amino groups, it is generally advantageous to blend polyisocyanates such that the isocyanate groups are present in an amount equal to or less than equivalent to the primary and/or secondary amino groups. More
40 preferably, a polyamine containing four or more primary and/or secondary amino groups and a polyisocyanate having an average number of functional groups (that is, the number of isocyanate groups/average molecular weight) of 2.5 or 2.5 - 6 are used and blended such that at least three amino groups of the polyamine are reacted with the isocyanate groups. Also in these cases, the total amount of the primary amino groups, the secondary amino groups and the tertiary amino groups before reaction is
45 preferably from 1.05 to 5 times the equivalent amount of the isocyanate groups.

(Mixing Ratio of Pigments and Other Ingredients)

50 The mixing ratio between the total amount of the polyamines and the polyisocyanates and the pigments, based on 100 % by weight of the total amount of the polyamines, the polyisocyanates and the pigments, has to be such that from 99.9 to 70 % by weight of the pigments are mixed with from 0.1 to 30 % by weight of the total amount of the polyamines and the polyisocyanates. A more preferred mixing ratio is from 99 to 80 parts by weight of the pigments based on from 1 to 20 parts by weight of the total amount
55 of the polyamines and the polyisocyanates.

If the amount of the polyamines and the polyisocyanates used is less than 0.1 % by weight, no sufficient effect of this invention can be attained. While on the other hand, if it exceeds 30 % by weight, the viscosity of the composition containing the dispersed pigment is significantly and undesirably increased.

(Mixing Ratio of Resins and Pigments)

The mixing ratio between the vehicle resins and the pigments in the composition containing the dispersed pigment according to this invention usually ranges from 98 to 10 parts by weight of the pigments based on from 2 to 90 parts by weight of the solid component in the vehicle resins in the preparation or the like for reasons of economy. A more preferred blending ratio ranges from 97 to 30 parts by weight of the pigments based on from 3 to 70 parts by weight of the solid component in the vehicle resins.

10 (Reaction of Polyamines and Polyisocyanates)

Vehicle resins generally employed in the paint or printing ink industries have hydroxyl groups or carboxyl groups as the functional groups, which are in most cases reactive with isocyanate groups. However, since the reactivity between the amines and the isocyanates is significantly higher than the reactivity between the vehicle resins and the isocyanates, if the reaction is carried out between the amines and the isocyanates in the presence of the vehicle resins or pigments, substantial reactions occur only between the amines and the isocyanates. This can be confirmed by determining the amount of unreacted amino groups after the reaction between the amines and the isocyanate by potentiometric titration as shown in Examples 2 and 3. That is, the amount of the unreacted amino groups is substantially equal to the difference between the amount of the amino groups and that of the isocyanate groups used for the reaction.

Although the amines and the isocyanates generally cause a rapid chemical reaction at a room temperature, the temperature may be increased or organotin compounds or the like may be used as a catalyst in a case where it is required to complete the chemical reaction between both of them more quickly.

Materials prepared by mixing and reacting the amines and the isocyanates in the absence of pigments and vehicles are generally difficult to be dissolved in the solvents usually employed in the paint and printing ink industries. For instance, in the case of polyamines and polyisocyanates are reacted under the absence of vehicle resins in a solvent such as toluene, precipitation is resulted. A composition containing dispersed pigment superior to conventional compositions can be obtained by adding vehicle resins, pigments and an optional organic solvent to the precipitate, and then dispersing.

While on the other hand, in the case of the polyamines and the polyisocyanates are reacted in solutions containing vehicle resins and, optionally, organic solvents, the materials resulting from the reaction are dissolved or finely dispersed in the solution of the resins. Particularly, in a case where the polyamines and the polyisocyanates are reacted at such a blending ratio as to leave the amino groups in the vehicle resins having polar functional groups such as carboxyl groups and, optionally, in organic solvents, the reaction products are dissolved more, which are excellent for dispersing the pigments.

It has been found that when the pigments are dispersed in a mixture comprising the reaction products of the polyamines and polyisocyanates, the vehicles resins and, optionally, organic solvents as described above, the reaction products can provide the effect of stabilizing the dispersed pigments.

(Preparation of Composition containing Dispersed Pigment)

A particularly preferred method for preparing a composition containing dispersed pigment comprises adding polyamines and polyisocyanates to a mixture of pigments, solution of vehicle resins and an optional organic solvent while the said mixture being dispersed, or comprises adding polyamines and polyisocyanates to a mixture of vehicle resins and an optional organic solvent, and then adding pigments to the said mixture, and after that, dispersing pigments.

As the dispersing equipment for pigments in this case, those dispersing equipments usually employed in the paint or printing industries, for example, sand grinding mill, ball mill, roll mill, attritor and dissolver can be used as required.

(Advantage of the Invention)

In accordance with this invention, a composition containing dispersed pigment excellent in dispersion stability and having preferred flowing property can be obtained in an extremely simple process.

Further, the composition containing the dispersed pigment according to this invention is applied to the

paint, (1) by the method of forming reaction products of the polyamines and the polyisocyanates having high dispersibility in the vehicle resins used, or (2) by the method of dispersing the pigments by mixing the vehicle resins into the reaction products of the polyamines and the isocyanates. This invention, when practiced in such embodiments, can provide various industrial advantages such as simplification of the production steps which have hitherto brought about problems in the prior art, as well as improvement in the dispersibility and the stability in dispersion of the pigments, elimination of the restriction on resins used together caused by the compatibility and the like.

Furthermore, since the blending ratio of the dispersing agent is from 0.1 to 30 % by weight based on total amount of the pigments and dispersing agent in this invention, while about 4.8 to 50 % by weight of dispersing agent based on total amount of the pigments and dispersing agent have been required in the prior art, the amount of vehicle resins used and the range for selecting them can be greatly extended.

Accordingly, the durability and other performance of the paint films when formed with the composition containing dispersed pigments according to this invention do not substantially suffer from undesired effects by the composition containing dispersed pigment. Paint, printing ink, and the like prepared by using the composition containing the dispersed pigment according to this invention can provide paint films excellent in gloss, distinctness of image, color strength, flooding and the like.

Differing from the dispersing agents of the prior art, the dispersing agent according to this invention can be synthesized in the process of dispersing the pigment through the direct mixing of specific starting materials with pigments, by which the composition containing dispersed pigment can be prepared in situ. Alternatively, the dispersing agent of this invention can previously be synthesized in a solvent, which can then be served for the preparation of the composition containing dispersed pigment. Furthermore, the dispersing agent of this invention can easily be synthesized in the presence of wide variety of vehicle resins for use in the paint or the like, through which the drawbacks involved in the conventional dispersing agents can be eliminated.

Embodiment of the Invention

The following examples of this invention and Comparative Examples shown below are given solely for the easy understanding of this invention, which are thus in no way restrictive.

In the following Examples and Comparative Examples, "part" means parts by weight and "%" means % by weight unless otherwise specified.

Example 1

50 parts of a short oil alkyd resin modified with coconut oil (acid value 8, a hydroxy value 80, 60 % solid content), 30 parts of methyl isobutyl ketone and 20 parts of Cinquasia red Y (trade name of products of quinacridone series organic pigment, manufactured by E.I. du Pont de Nemours & Company) were subjected to dispersing treatment by a sand grind mill for 10 min and, thereafter, 0.28 parts of ethylene diamine were added to the thus formed mixture. Further, while continuing the dispersing treatment, 1.22 parts of 4,4'-methylene bis [cyclohexylisocyanate] (hydrogenated MDI) were added to a mixture formed by the mixing treatment as described above, and the dispersing treatment was continued for further 20 minutes. A composition containing the dispersed pigment (1) was thus prepared.

For comparison, the same 50 parts of the coconut oil modified alkyd resin, 30 parts of the methyl isobutyl ketone and 20 parts of the Cinquasia red Y were subjected to the dispersing treatment in a sand grind mill for 30 minutes to prepare a composition containing the dispersed pigment (2). The viscosity of the composition containing dispersed pigment (1) and that of the composition containing dispersed pigment (2) were measured by a Model E viscometer (manufactured by Tokyo Keiki Co., Ltd.). The results are shown in Table 1.

Table 1

Rotor Speed	5 rpm	50 rpm
Composition containing dispersed pigment (1)	160 cps	145 cps
Composition containing dispersed pigment (2)	696 cps	132 cps

It is apparent from the results of the above-described experiment that the composition containing dispersed pigment (1) according to this invention has an extremely excellent flowing property with lower thixotropy.

Example 2

0.63 parts of tetraethylenepentamine were added to a mixture of 50 parts of the coconut oil modified alkyd resin as used in Example 1 and 30 parts of Solvesso 100 (trade name of products available from Esso Standard Co., Ltd.) and 0.87 parts of 4,4'-methylene bis [cyclohexylisocyanate] (hydrogenated MDI) were added to the thus obtained mixture being stirred with a dissolver. When measuring the amount of amino groups contained in the thus obtained resin solution in acetic acid by way of potentiometric titration using perchloric acid as a titration reagent, 0.123 mmol of perchloric acid was required for neutralizing 1 g of the resin solution. The amount is equal to the difference between the amount of the amino groups in the tetraethylene-pentamine and the amount of the isocyanate groups added.

Since it was confirmed that the alkyd resin and Solvesso 100 had no amino groups by way of the potentiometric titration, it was ensured that the isocyanate groups added had reacted partially with the amino groups of tetraethylenepentamine. 20 parts of the same pigments as in Example 1 were added to 81.5 parts of the resin solution as described above and the thus obtained mixture was subjected to dispersing by a sand grinding mill for 30 minutes to thereby obtain a composition containing the dispersed pigment (3).

Further, a composition containing dispersed pigment (4) was obtained with the same procedures as above except for using 0.4 parts of tetraethylenepentamine and 1.1 parts of 4,4'-methylene bis [cyclohexylisocyanate] (hydrogenated MDI). Further, a composition containing dispersed pigment (5) was obtained in the same procedures while replacing tetraethylenepentamine with 0.28 parts of ethylene diamine and using 1.22 parts of 4,4'-methylene bis [cyclohexylisocyanate] (hydrogenated MDI).

While on the other hand, 20 parts of the same pigment as described above were added to 50 parts of the alkyd resin and 30 parts of the Solvesso 100 also as described above and the thus obtained mixture was subjected to the dispersing treatment in a sand grind mill for 30 minutes to obtain a composition containing dispersed pigment (6).

The viscosity for each of the compositions containing dispersed pigment was measured by a Model E viscometer manufactured by Tokyo Keiki Co., Ltd. The results are shown in Table 2.

Table 2

	Rotor Speed	5 rpm	50 rpm
5	Composition containing dispersed pigment (3)	387 cps	315 cps
10	Composition containing dispersed pigment (4)	365 cps	309 cps
	Composition containing dispersed pigment (5)	872 cps	415 cps
15	Composition containing dispersed pigment (6)	731 cps	230 cps

The compositions containing dispersed pigment (3) and (4) exhibited excellent flowing property with lower thixotropy.

50 parts of the same coconut oil modified alkyd resin as described above and 30 parts of Uvan 128, i.e., trade name of melamine formaldehyde resin varnish manufactured by Mitsui Toatsu Chemical Co., Ltd., to thereby prepare a baking type alkyd melamine resin paint.

Each of the paints as described above was diluted with a thinner to a viscosity suitable for spraying and then spray coated on a tin plate. The thus coated tin plate was kept in the air at 140°C for 30 minutes and, thereafter, 20° gloss and 60° gloss for the paint film were measured.

Further, after applying each of the diluted paints on the tin plate by way of flow coating which means such a coating process of putting approx. 5 cc of paint on a tin plate sized 50 mm x 150 mm, coating the tin plate by disposing the plate vertically thereby causing the paint to flow downwardly and then keeping as it is for 10 minutes, the coated tin plate was kept in air at 140°C for 30 minutes and the paint film was baked. The 20° gloss of the paint film thus obtained was measured. The results are as shown in Table 3.

Table 3

	Spray coating		Flow coating
	20°	60°	20°
35	Composition containing dispersed pigment (3)	85	79
40	Composition containing dispersed pigment (4)	87	82
45	Composition containing dispersed pigment (5)	77	45
	Composition containing dispersed pigment (6)	72	22

It is apparent from Table 3 that the compositions containing dispersed pigment (3) and (4) are excellent, with the composition containing dispersed pigment (4) being particularly excellent.

While tetraethylenepentamine and polyisocyanate compounds were blended such that two out of the five amino groups of tetraethylenepentamine were reacted with the isocyanate groups in the composition containing dispersed pigment (3), tetraethylenepentamine and polyisocyanate compounds were blended such that four amino groups of the tetraethylenepentamine were reacted in the composition containing dispersed pigment (4).

In this way, by reacting more amino groups possessed in the polyamine, the effect of this invention can

further be improved.

In the composition containing the dispersed pigment (5), ethylenediamine was used and it was blended with the polyisocyanate compound such that all of the amino groups were reacted with the isocyanate groups. Although the composition containing dispersed pigment (5) was superior as compared with the composition containing dispersed pigment (6) of this invention, it was inferior to the compositions containing dispersed pigment (3) and (4).

These experiments demonstrated the fact that the use of amino groups in excess with respect to the isocyanate groups is preferred so that the reaction product of the polyamine and the polyisocyanate contains amino groups.

Example 3

0.32 parts of tetraethylenepentamine were added to a mixture of 50 parts of the coconut oil modified alkyd resin as used in Example 1 and 30 parts of Solvesso 100 (trade name of products manufactured by Esso Standard Co., Ltd.). 1.18 parts of a trimer of hexamethylene-1,6-diisocyanate having a biuret structure, that is, Takenate D-165N-90CX (trade name of products available from Takeda Chemical Industries Co., Ltd.) (amine equivalent 200) was added to the thus obtained mixture under stirring by a dissolver. The mixture was stirred by the dissolver for further 30 minutes, produced a resin solution (A).

The amount of the amino groups contained in one g of the thus obtained resin solution (A) was measured by the method as described in Example 2. It was equivalent to 0.03 mmol of perchloric acid, which was equal to the difference between the amount of the amino groups and that of the isocyanate groups added.

20 parts of the same pigment as in Example 1 were added to 81.5 parts of the resin solution (A) and the thus obtained mixture was subjected to a dispersing treatment by the sand grind mill for 30 minutes to form a composition containing dispersed pigment (7). The viscosity was measured by a Model E viscometer manufactured by Tokyo Keiki Co., Ltd. The composition containing dispersed pigment (7) had a viscosity lower than that for each of the compositions containing the dispersed pigment in Example 2 as shown in Table 4 and exhibited excellent flow property with lower thixotropy.

Table 4

Rotor Speed	5 rpm	50 rpm
Composition containing dispersed pigment (7)	235 cps	218 cps

To 100 parts of the composition containing dispersed pigment (7) as described above, were added the same 50 parts of the coconut oil modified alkyd resin and 30 parts of the melamine formaldehyde resin varnish as in Example 2 to prepare a baking type melamine alkyd resin paint. The paint was diluted with a thinner to a viscosity suitable for spraying and spray coated onto a tin plate. The thus obtained tin plate was kept in air at 140°C for 30 minutes, which baked the paint film. 20° gloss and 60° gloss of the thus obtained paint film, as well as the 20° gloss of the paint film obtained by the flow coating were measured. The results are shown in Table 5.

Table 5

	Spray coating		Flow coating
	20° gloss	60° gloss	20° gloss
Composition containing dispersed pigment (7)	89	93	84

The composition containing dispersed pigment (7) exhibited superior results to the composition containing dispersed pigment (4) in Example 2 by using polyfunctional polyisocyanate having more than 2 isocyanate groups.

Example 4

0.63 parts of tetraethylenepentamine were applied to 30 parts of methyl isobutyl ketone and the thus obtained mixture was stirred in a dissolver. 0.87 parts of 4,4'-methylene bis [cyclohexylisocyanate] (hydrogenated MDI) were applied to the above-mentioned mixture under stirring. A rapid exothermic reaction occurred to form white precipitates. To the thus obtained mixture of reaction product and methyl ethyl ketone, were applied the same 50 parts of the coconut oil - modified alkyd resin and 20 parts of pigments as used in Example 1 and 120 parts of glass beads of 1.5 mm ϕ . The thus obtained mixture was subjected to a dispersing treatment in a paint shaker for 2 hours to form a composition containing dispersed pigment (8).

While on the other hand, the same 50 parts of the coconut oil - modified alkyd resin and 0.63 parts of tetraethylenepentamine as described above were added to 30 parts of methyl isobutyl ketone, and 0.87 parts of 4,4'-methylene bis [cyclohexylisocyanate] (hydrogenated MDI) were added to the thus formed mixture under stirring by a dissolver, followed by continued stirring for further 30 minutes. To the thus obtained resin solution, were added 20 parts of the same pigment as in Example 1 and 120 parts of glass beads of 1.5 mm ϕ and the obtained mixture was shaken in a paint shaker for 2 hours to prepare a composition containing dispersed pigment (9).

To each 100 parts of the composition containing dispersed pigment (2) in Example 1 and compositions containing dispersed pigments (8) and (9) in this example, were added the same 50 parts of the coconut oil modified alkyd resin and 30 parts of melamine resin varnish as in Example 2, to prepare baking type melamine alkyd resin paints, respectively. The paints were diluted with a thinner to a viscosity suitable for spraying. Each of the thus obtained diluted paints was flow-coated on a tin plate (after putting about 5 cc of paint to the upper part of a tin plate sized 50 mm x 150 mm, the paint was caused to flow downwardly by disposing the tin plate vertically to coat the tin plate and then kept as it was for 10 minutes). The thus coated tin plate was kept in air at 140°C for 30 minutes and the paint film was baked. The 20° gloss of the thus obtained paint film is shown in the following Table 6.

Table 6

	20° gloss
Composition containing dispersed pigment (2)	29
Composition containing dispersed pigment (8)	69
Composition containing dispersed pigment (9)	84

As apparent from Table 6, the compositions containing dispersed pigment (8) and (9) had excellent performance, with the composition containing dispersed pigment (9) being particularly preferred.

Example 5

To each 81.5 parts of the resin solution (A) in Example 3, was added each 20 parts of Novoperm orange HL-70 (trade name of azo series pigment products, manufactured by Hoechst A.G.), Hostaperm yellow H-3G (trade name of azo series organic pigment of products manufactured by Hoechst A.G.) and Paliogen red L-3910HD (trade name of perylene series organic pigment of products, manufactured by BASF AG), respectively. The thus obtained mixtures were subjected to the dispersing treatment in a ball mill for 24 hours to prepare compositions containing dispersed pigment (10), (12) and (14), respectively.

For the comparison, 20 parts of each of the pigments as described above were added to 50 parts of the coconut oil modified alkyd resin and 30 parts of Solvesso 100 (trade name of products manufactured by Esso Standard Co., Ltd.). The thus obtained mixtures were subjected to the dispersing procedures in a ball mill for 24 hours to form compositions containing dispersed pigment (11), (13) and 15.

- 5 The viscosity for each of the compositions containing dispersed pigment is shown in the following Table 7. Further, 50 parts of coconut oil modified alkyd resin and 30 parts of melamine formaldehyde resin varnish were added to the respective compositions containing dispersed pigment as in Example 2, to prepare melamine alkyd resin paints. The thus prepared melamine alkyd resin paints were spray coated on tin plates and the thus coated tin plates were kept in air at 140°C for 30 minutes to effect paint films
10 baking. The 20° gloss and the 60° gloss of the paint film thus obtained were measured. The results are also shown in the following Table 7.

Table 7

Pigment	Composition containing dispersed pigment	Viscosity		Spray coating	
		5 rpm	50 rpm	20° gloss	60° gloss
Novoperm orange HL-70	(10)	127 cps	122 cps	88	93
	(11)	510 cps	166 cps	80	91
Hostaperm yellow H-3G	(12)	341 cps	290 cps	88	92
	(13)	1134 cps	324 cps	76	90
Paliogen red L-3910HD	(14)	1898 cps	615 cps	86	91
	(15)	2365 cps	586 cps	75	89

- 30 From the experiment as described above, it was found that the composition containing the dispersed pigment according to this invention had excellent performance compared with conventional dispersing method. of the pigments.

35 Example 6

- 0.56 parts of diethylenetriamine were added to a mixture of 45 parts of the same alkyd resin in Example 1 and 45 parts of xylene and the thus obtained mixture was stirred by a dissolver. 3.65 parts of an adduct of 3 mol of hexamethylene diisocyanate and 1 mol of trimethylol propane, that is, Coronate HL (trade name of products containing 25 % ethyl acetate and 12.5 % NCO, manufactured by Nippon Polyurethane Industries Co., Ltd.) were added to the above-mentioned mixture under stirring by a dissolver, to obtain a resin solution. Then, 10 parts of carbon black MA-100 (trade name of products available from Mitsubishi Chemical Industries Ltd.) were added to the resin solution and the thus obtained mixture was subjected to a dispersing treatment in a sand grind mill for 30 minutes. In this manner, a composition containing dispersed pigment (16) was obtained. For the comparison, a composition containing dispersed pigment (17) was prepared in the same procedures as described above without adding polyamine and polyisocyanate.

The viscosity for each of the compositions was measured by a rotary Model E viscometer (manufactured by Tokyo Keiki Co., Ltd.). The results are shown in the following Table 8.

Table 8

Rotor Speed	5 rpm	50 rpm
Composition containing dispersed pigment (16)	75 cps	68 cps
Composition containing dispersed pigment (17)	895 cps	173 cps

Example 7

50 parts of Acrylic A-405 (trade name of acrylic resin varnish products, available from Dainippon Ink & Chemicals, Inc.), 50 parts of xylene, 20 parts of Hostaperm yellow H-3G (trade name of products available from Hoechst AG) were subjected to dispersing treatment in a grind mill for five minutes. 0.32 parts of tetraethylenepentamine were added to the thus obtained mixture and 1.72 parts of Sumidur (trade name of products containing 16.5 % NCO, 12.5 % of methyl glycol acetate and 12.5 % of xylene, manufactured by Sumitomo Bayer Urethane Co. Ltd.) were added to the thus obtained mixture under the dispersing treatment and further subjected to a dispersing treatment for 25 minutes to obtain a dispersed paste (18).

For the comparison, a composition containing dispersed pigment (19) was prepared without adding amine and isocyanate. 90 parts of Acrylic A-105 and 60 parts of Super Beckamine J-820 (trade name of products of melamine resin varnish, manufactured by Dainippon Ink & Chemical Industries Co., Ltd.) were added to the compositions containing dispersed pigments respectively, to prepare baking type melamine acrylic resin paints. Each of the paints was coated on a glass plate by using a 6 mil applicator and baked at 150° C for 30 minutes. The 20° gloss and the 60° gloss for the obtained paint film were measured. The results are shown in Table 9.

Table 9

	20° gloss	60° gloss
Composition containing dispersed pigment (18)	88	94
Composition containing dispersed pigment (19)	72	90

Table 9 shows that the composition containing dispersed pigment (18) according to this invention is superior to the Comparative Example, that is, the composition containing dispersed pigment (19).

Example 8

25 parts of toluene and a further 20 parts of Transparent oxide red 30-1005 (trade name of products for transparent iron oxide pigment, manufactured by The Hilton-Davis Chemical Co.) were added to 60 parts of Acrylic A-405 (trade name of products manufactured by Dainippon Ink & Chemicals Industries Co., Ltd.), and the thus obtained mixture was subjected to a dispersing treatment by the sand grind mill for five minutes. 0.29 parts of tetraethylenepentamine were added to the thus obtained mixture and, while continuing the dispersing treatment to the mixture, 1.21 parts of Coronate EH (trade name of products containing 21.3 % NCO manufactured by Nippon Polyurethane Industries Co., Ltd.) were added and subjected to dispersing treatment for 25 minutes. In this way, a composition containing dispersed pigment (20) was obtained.

For the comparison, a composition containing dispersed pigment (21) was prepared by the same dispersing treatment by a sand grind mill without adding amine and isocyanate.

The viscosity for each of the compositions containing dispersed pigment was measured by a rotary Model E viscometer (manufactured by Tokyo Keiki Co., Ltd.), and 80 parts of Acrylic A-405 (trade name of products manufactured by Dainippon Ink & Chemical Industries Co., Ltd.) and 60 parts of Super Beckamine J-820 (trade name of products manufactured by Dainippon Ink & Chemical Industries Co., Ltd.) were added respectively to both of the compositions containing the dispersed pigment, to prepare baking type melamine acrylic resin paints. Each of the thus obtained paints was coated on a glass plate using a 6 mil applicator and baked at 150°C for 30 minutes. The 20° gloss and the 60° gloss for the paint film thus obtained were measured. The results are shown in Table 10.

Table 10

	Viscosity		Gloss	
	5 rpm	50 rpm	20°	60°
Composition containing dispersed pigment (20)	1821 cps	1301 cps	126	119
Composition containing dispersed pigment (21)	2900 cps	1208 cps	117	108

Table 10 shows that the composition containing dispersed pigment (20) according to this invention is superior to the Comparative Example, that is, the composition containing dispersed pigment (21).

Comparative Example 1

The composition containing dispersed pigment according to this invention, the composition containing dispersed pigment prepared by using the dispersing agent described in the example of Japanese Patent Laid-Open No. 160396/1975 and a composition containing dispersed pigment prepared by using a dispersing agent described as Agent 1 in the British Patent Specification No. 1393401 were compared with each other. Each of the dispersing agents is referred to hereinafter with the numbers as described below.

Dispersing agent 1	Japanese Patent Laid-Open No. 160396/1975	Example 1
Dispersing agent 2	Japanese Patent Laid-Open No. 160396/1975	Example 8
Dispersing agent 3	British Patent No. 139401	Agent 1

To 20 parts of Cinquasia red Y (trade name of products available from E. I. du Pont de Nemours & Co.) were added 10 parts of each of the dispersing agents as the solid content and then Solvesso 100 (trade name of products available from Esso Standard Co., Ltd.), so as to make up the entire amount to 60 parts. The thus obtained mixture was subjected to dispersing treatment by a sand grind mill for 30 minutes and, thereafter, 40 parts of the coconut oil modified alkyd resin as described in Example 1 was added and subjected to a dispersing treatment for 10 minutes to obtain compositions containing dispersed pigment (22), (23) and (24) in order of the number of dispersing agent. To each 100 parts of the compositions containing dispersed pigment (3) and (4) in Example 2 and compositions containing dispersed pigment (22), (23) and (24) as described above, were added the same 50 parts of the coconut oil modified alkyd resin and 30 parts of the melamine resin varnish as in Example 2, to prepare baking type alkyd melamine resin paints. Each of the paints was diluted with a thinner to a viscosity suitable for spraying, coated onto a tin plate by way of flow coating and spray-coated and baked at 140°C for 30 minutes. Then, the 20° gloss on

the thus obtained paint film was measured. The results are shown in Table 11.

Table 11

	Flow coating 20' gloss	Spray coating 20' gloss
5 Composition containing dispersed pigment (3)	79	85
10 Composition containing dispersed pigment (4)	82	87
15 Composition containing dispersed pigment (22)	41	75
Composition containing dispersed pigment (23)	33	73
20 Composition containing dispersed pigment (24)	47	80

Table 11 shows that the dispersion composition according to this invention, that is, the compositions containing dispersed pigments (3) and (4) are more excellent.

Claims

(1) A composition containing a dispersed pigment comprising, as a dispersing agent, one or more of reaction products obtained from at least one polyamines having two or more of primary amino groups and / or secondary amino groups and at least one polyisocyanate having two or more of isocyanate groups, wherein the polyamines are selected from the group consisting of ethylene diamine, 1,3-propylene diamine, hexamethylene diamine, diethylene triamine, triethylene tetramine, tetraethylene pentamine, pentaethylene hexamine, bisaminopropyl piperadine, bisamino pyridine, xylylene diamine, metaphenylene diamine, 4,4'-diaminodiphenyl methane and polyethyleneimine.

(2) A composition containing a dispersed pigment comprising, as a dispersing agent, one or more of reaction products obtained from at least one polyamine having two or more primary amino group and / or secondary amino groups and at least one polyisocyanate having two or more of isocyanate groups and, further, a pigment and an organic solvent, wherein the polyamines are selected from the group consisting of ethylene diamine, 1,3-propylene diamine, hexamethylene diamine, diethylene triamine, triethylene tetramine, tetraethylene pentamine, pentaethylene hexamine, bisaminopropyl piperadine, bisamino pyridine, xylylene diamine, metaphenylene diamine, 4,4'-diaminodiphenyl methane and polyethyleneimine.

(3) A composition containing a dispersed pigment comprising one or more of reaction products obtained from at least one polyamine having two or more primary amino group and / or secondary amino groups and at least one polyisocyanate having two or more of isocyanate groups, a pigment, a vehicle resin and, optionally, an organic solvent, wherein the polyamines are selected from the group consisting of ethylene diamine, 1,3-propylene diamine, hexamethylene diamine, diethylene triamine, triethylene tetramine, tetraethylene pentamine, pentaethylene hexamine, bisaminopropyl piperadine, bisamino pyridine, xylylene diamine, metaphenylene diamine, 4,4'-diaminodiphenyl methane and polyethyleneimine.

(4) A composition containing a dispersed pigment as defined in any one of claims 1 to 3, wherein the polyisocyanate groups are selected from the groups consisting of aromatic polyisocyanates, aliphatic polyisocyanates and cycloaliphatic polyisocyanates.

(5) A composition containing a dispersed pigment as defined in any one of claims 1 to 3, wherein the polyisocyanates are selected from the group consisting of toluylene diisocyanate, 4,4'-diphenylmethane diisocyanate, xylylene diisocyanate, hexamethylene diisocyanate, 4,4'-methylene bis cyclohexylisocyanate, hydrogenated TDI, hydrogenated XDI and isophorone diisocyanate.

(6) A composition containing dispersed pigment as defined in any one of claims 1 to 3, wherein the average number of functional groups of the polyisocyanate groups is from 2.5 to 6.

(7) A composition containing a dispersed pigment as defined in any one of claims 1 to 3, wherein the polyamines are blended in such an amount as the amino groups thereof are in excess of a stoichiometrical amount relative to the isocyanate groups contained in the polyisocyanates.

(8) A composition containing a dispersed pigment as defined in claim 7, wherein the polyamines are blended in such an amount as containing amino groups from 1.05 to 5 times of a stoichiometrically equivalent amount relative to the isocyanate groups contained in the polyisocyanates.

(9) A composition containing a dispersed pigment as defined in any one of claims 1 to 8, wherein the polyamines and the polyisocyanates are blended in total by an amount from 0.1 to 30 parts by weight based on 99.9 to 70 parts by weight of the pigment.

(10) A composition containing a dispersed pigment as defined in any one of claims 3 to 9, wherein the vehicle resin is selected from the group consisting of alkyd resins, polyester resins, acrylic resins, polyamide resins, as well as vinyl resins such as polyvinyl chloride, polyvinyl acetate and chlorinated polyolefine.

(11) A composition containing a dispersed pigment as defined in any one of claims 2 to 10, wherein the organic solvent is selected from the group consisting of hydrocarbons, esters, ketones and ethers.

20

25

30

35

40

45

50

55



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 88 10 6425

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
Y	DE-A-2 041 033 (ICI) * Claims 1-3; page 6, lines 1-4; page 6, lines 13-16; page 8, lines 1-4; page 8, lines 14-21; page 9, lines 9-11; page 10, paragraph 2; page 14, lines 14-19 *	1,2,4, 11	C 09 D 17/00 C 09 B 67/00
A	---	10	
Y,D	GB-A-1 393 402 (ICI) * Page 1, lines 9-20; page 2, lines 88-102; page 2, lines 110-114 *	1,2,4, 11	
A	---	5	
A	EP-A-0 014 907 (BASF) -----		
			TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			C 09 D C 09 B
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 09-09-1988	Examiner GIRARD Y.A.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

ETO FORM 1503 01.82 (P0401)